



2845 W. 48TH PLACE
CHICAGO, ILLINOIS 60632
PHONE (773) 523-7000
FAX (773) 523-0965
www.westexinc.com

SPECIFICATION

FABRIC:	Style 301 INDURA® Ultra Soft® 88% Cotton/12% High Tenacity Nylon Rugged Shirting/Tropical Coverall Weight
WIDTH – (Inches, Minimum, Selvedge included): ASTM D3774	59
YARNS PER INCH – (Minimum, Warp and Fill): ASTM D3775	92 x 45
WEIGHT – (Oz/sq yd, Minimum): ASTM D3776	7.0
BREAKING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D5034	90 x 60
TEARING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D1424	5.5 x 5.0
SHRINKAGE – (% , Maximum): Federal Test Standard 191A Method 5550 Warp and Fill	3.0
FLAMMABILITY: ASTM D6413 After Flame, Seconds (Maximum) Char Length, Inches (Maximum)	2.0 5.0

This fabric meets the requirements of ASTM F1506, NFPA 70E Level 2, NFPA 1977, NFPA 2112, and OSHA 29 CFR 1910.269.

INDURA® and INDURA® Ultra Soft® are trademarks of Westex Inc.

1/29/03

SPECIALTY AND FLAME RESISTANT FABRICS SINCE 1919

