

SPECIFICATION

FABRIC:	Style 451 INDURA® Ultra Soft® 88% Cotton/12% High Tenacity Nylon Rugged Twill	
WIDTH – (Inches, Minimum, Selvedge included): ASTM D3774		59
YARNS PER INCH – (Minimum, Warp and Fill): ASTM D3775		90 x 50
WEIGHT – (Oz/sq yd, Minimum): ASTM D3776		9.0
BREAKING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D5034		130 x 100
TEARING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D1424		7.0 x 6.5
SHRINKAGE – (% , Maximum): Federal Test Standard 191A Method 5550 Warp and Fill		3.0
FLAMMABILITY: ASTM D6413		
After Flame, Seconds (Maximum)		2.0
Char Length, Inches (Maximum)		5.0

This fabric meets the requirements of ASTM F1506, NFPA 70E Level 2, NFPA 1977, NFPA 2112, CGSB 155.20 and OSHA 29 CFR 1910.269.

INDURA® and INDURA® Ultra Soft® are trademarks of Westex Inc.

07/30/02