

SPECIFICATION

| | | |
|---|--|-----------|
| FABRIC: | Style 961 INDURA® Ultra Soft® 88% Cotton/12% High Tenacity Nylon Rough House Duck | |
| WIDTH – (Inches, Minimum, Selvedge included): ASTM D3774 | | 59 |
| YARNS PER INCH – (Minimum, Warp and Fill): ASTM D3775 | | 85 x 25 |
| WEIGHT – (Oz/sq yd, Minimum): ASTM D3776 | | 11.0 |
| BREAKING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D5034 | | 130 x 120 |
| TEARING STRENGTH – (Pounds, Minimum, Warp and Fill): ASTM D1424 | | 6.0 x 8.0 |
| SHRINKAGE – (% , Maximum): Federal Test Standard 191A Method 5550 Warp and Fill | | 3.0 |
| FLAMMABILITY: ASTM D6413 | | |
| After Flame, Seconds (Maximum) | | 2.0 |
| Char Length, Inches (Maximum) | | 5.0 |

This fabric meets the requirements of ASTM F1506, NFPA 70E Level 2,
 CGSB 155.20 and OSHA 29 CFR 1910.269.

INDURA® and INDURA® Ultra Soft® are trademarks of Westex Inc.